



ESL ELECTRO-SCIENCE

CERAMIC TAPES &
THICK-FILM MATERIALS

416 EAST CHURCH ROAD
KING OF PRUSSIA, PA 19406-2625 USA F: 610.272.6759

T: 610.272.8000

www.electroscience.com

POLYMER SILVER CONDUCTOR

19102-A

RoHS Compliant* High Temperature Conductor

ESL 19102-A is a solderable high-temperature, low-resistivity silver polymer conductor, that provides good adhesion and thermal stability. It is designed for use as solderable pads for LED and as a resistor termination for heating element on ceramic and polyimide film. The ESL 19102-A can also be used on ESL 14401, 14402-A and 14404 polymer dielectric on metal substrates.

Please review the Application Note: Polyimide Thick Film Materials before using this product.

PASTE DATA

RHEOLOGY:	Thixotropic, screen-printable paste
VISCOSITY: (Brookfield RVT, ABZ spindle, 10 rpm, 25.5°C ± 0.5°C)	150 ± 50 Pa-s
SHELF LIFE: (at 0°C)	3 months
(at -18°C)	12 months

PROCESSING

SCREEN MESH / EMULSION:	200 / 20-30 µm
LEVELING TIME:	5-10 minutes
DRYING at 125°C:	10-15 minutes
CURING CYCLE:	320°C / 150 minutes (10-15°C/min. rise)
SUBSTRATE OF CALIBRATION:	aluminum
THINNER	ESL 455

19102-A 1401-C

ESL Affiliates

ESL China • Room#2712 • Far East International Plaza • No.317 Xianxia Road, • Changning District • Shanghai, China 200051 • Tel: +86-21-6237-0336 • Fax: +86-21-6237-0338 • eslchina@eslshanghai.net

ESL Europe • 8 Commercial Road • Reading, Berkshire, England RG2 0QZ • Tel: +44-118-918-2400 • Fax: +44-118-986-7331 • sales@esleurope.co.uk

ESL in Korea • AMT • South Korea • Tel: +82-31-466-0651 • Fax: +82-31-466-0658 • yumikim@esl-amt.co.kr

ESL-Nippon • Sukegawa Bldg 6th floor • 1-3-4 Yanagibashi • Taito-ku • Tokyo, Japan 111-0052 • Tel: +81-3-3864-8521 • Fax: +81-3-3864-9270 • sales@esl-nippon.co.jp

ESL Taiwan • 14F, No. 168, Dunhua N. Road • Sungshan District • Taipei 105, Taiwan • Tel: +886-975-553-612 • dshih@esl-taipei.com

See Caution and Disclaimer on other side.

TYPICAL PROPERTIES

CURED THICKNESS:	10-15 μm
RESISTIVITY: (12 μm cured thickness)	< 12 $\text{m}\Omega/\text{sq.}$
COMPATIBLE MATERIALS:	ESL 14401,14402 and 14404 dielectric

19102-A 1401-C

* Complies with RoHS, ELV, WEEE and CHIP 3 EC directives.

CAUTION: Proper industrial safety precautions should be exercised in using these products. Use with adequate ventilation. Avoid prolonged contact with skin or inhalation of any vapors emitted during use or heating of these compositions. The use of safety eye goggles, gloves or hand protection creams is recommended. Wash hands or skin thoroughly with soap and water after using these products. Do not eat or smoke in areas where these materials are used. Refer to appropriate MSDS sheet.

DISCLAIMER: The product information and recommendations contained herein are based on data obtained by tests we believe to be accurate, but the accuracy and completeness thereof is not guaranteed. No warranty is expressed or implied regarding the accuracy of these data, the results obtained from the use hereof, or that any such use will not infringe any patent. Electro-Science assumes no liability for any injury, loss, or damage, direct or consequential arising out of its use by others. This information is furnished upon the condition that the person receiving it shall make their own tests to determine the suitability thereof for their particular use, before using it. User assumes all risk and liability whatsoever in connection with their intended use. Electro-Science's only obligation shall be to replace such quantity of the product proved defective.
