



Electro-Science Laboratories, Inc.

416 East Church Road • King of Prussia, PA 19406-2625, U.S.A
610-272-8000 • Fax: 610-272-6759 • www.ElectroScience.com • Sales@ElectroScience.com

CERMET PLATINUM CONDUCTOR

5544

ESL 5544 is a screen printable, fritted Pt conductor for use on 96% alumina substrates in resistance-thermometer and heater applications. The TCR of the fired film is more than 3300 ppm/°C. The change of resistance is linear over the range of -50°C to +500°C.

PASTE DATA

RHEOLOGY:	Thixotropic, screen printable paste
VISCOSITY: (Brookfield RVT, ABZ Spindle, 10 rpm, 25.5°C±0.5°C)	160±25 Pa·s
METALLIC PHASE:	platinum
BONDING MECHANISM:	Fritted
SHELF LIFE:	6 Months

PROCESSING

SCREEN/MESH/EMULSION:	325/37.5 μm
LEVELING TIME: (25°C)	5-10 minutes
DRYING AT 125°C:	10-15 minutes
FIRING RANGE:	980°C-1300°C
OPTIMUM:	1200°C
CALIBRATION TEMPERATURE:	980°C
TIME AT PEAK:	10 minutes
SUBSTRATE OF CALIBRATION:	96% alumina
THINNER:	ESL 401

5544 0107-C

ESL Affiliates

Japan: ESL-Nippon Company, Ltd. • Sukegawa Bldg. • 6th floor • 3-4 Yanagibashi 1-chome • Taito-ku • Tokyo 111, Japan • Tel: (011-81)-3-3864-8521 • Fax: (011-81)-3-3864-9270
NipponSales@ESLNippon.com

China: Shanghai Agmet Electro-Science Laboratory Ltd. • Second Floor Bldg. 12A1 • #223 North Fe Te Road • Waigaoqiao Free Trade Zone • Shanghai, China
Tel: (011-86)-21-5866-0497 • Fax: (011-86)-21-5866-0497 • ShanghaiSales@ShanghaiESL.com

Europe: Agmet, Ltd. • 8 Commercial Road • Reading, Berkshire, England RG2 0QZ • Tel: (011-44)-118-918-2400 • Fax: (011-44)-118-986-7331 • Sales@ESLEurope.co.uk

See Caution and Disclaimer on other side.

TYPICAL PROPERTIES

FIRED FILM THICKNESS:	6-9 μm
RESISTIVITY:	$\leq 70 \text{ m}\Omega/\text{square}$
HOT TCR: (25°C to +125°C)	$\geq 3300 \text{ ppm}/^\circ\text{C}$
COLD TCR: (25°C to -55°C)	$\geq 3300 \text{ ppm}/^\circ\text{C}$
PRINTING RESOLUTION: (Line/Space)	125 μm x 125 μm

5544 0107-C

CAUTION: Proper industrial safety precautions should be exercised in using these products. Use with adequate ventilation. Avoid prolonged contact with skin or inhalation of any vapors emitted during use or heating of these compositions. The use of safety eye goggles, gloves or hand protection creams is recommended. Wash hands or skin thoroughly with soap and water after using these products. Do not eat or smoke in areas where these materials are used. Refer to appropriate MSDS sheet.

DISCLAIMER: The product information and recommendations contained herein are based on data obtained by tests we believe to be accurate, but the accuracy and completeness thereof is not guaranteed. No warranty is expressed or implied regarding the accuracy of these data, the results obtained from the use hereof, or that any such use will not infringe any patent. Electro-Science assumes no liability for any injury, loss, or damage, direct or consequential arising out of its use by others. This information is furnished upon the condition that the person receiving it shall make their own tests to determine the suitability thereof for their particular use, before using it. User assumes all risk and liability whatsoever in connection with their intended use. Electro-Science's only obligation shall be to replace such quantity of the product proved defective.
