



ESL ELECTROSCIENCE

CERAMIC TAPES &
THICK-FILM MATERIALS

416 EAST CHURCH ROAD
KING OF PRUSSIA, PA 19406-2625, U.S.A

T: 610-272-8000
F: 610-272-6759

www.electroscience.com

CO-FIRING PLATINUM CONDUCTOR

5571

**RoHS compliant* co-fireable conductor
designed for use as a heater in planar sensors**

ESL 5571 is a platinum conductor designed to be co-fired with alumina tape at high temperatures.

PASTE DATA

RHEOLOGY: Thixotropic, screen-printable pastes
VISCOSITY: 75 ± 15 Pa•s
(Brookfield HBT, cone/plate, 38.4 sec⁻¹ at 25.0°C ± 0.5°C)
SHELF LIFE: 6 months

TYPICAL PROPERTIES

SCREEN MESH/EMUSLION: 325 mesh / 25 ± 5 µm
RESISTIVITY: (12.5 µm fired thickness) 40 ± 5 mΩ/square
FIRING RANGE: 1500°C ± 10°C
see profile on back
TIME AT PEAK TEMPERATURE: 120 min.
SODIUM CONCENTRATION: ≤ 50 ppm
SUBSTRATE OF CALIBRATION: alumina tape

5571 1004-A


ESL Affiliates

ESL China • Rm#1707, Tower A • City Center of Shanghai • 100 Zunyi Road • Shanghai, China 200051 Tel: (011-86)-21-62370336 • Fax: (011-86)-21-62370338 • eslchina@eslshanghai.com

ESL Europe • 8 Commercial Road • Reading, Berkshire, England RG2 0QZ • Tel: (011-44)-118-918-2400 • Fax: (011-44)-118-986-7331 • Sales@ESLEurope.co.uk

ESL Nippon • Sukegawa Bldg • 6th floor • 3-4 Yanagibashi 1-chome • Taito-ku • Tokyo 111, Japan • Tel: (011-81)-3-3864-8521 • Fax: (011-81)-3-3864-9270 • Sales@ESL-Nippon.co.jp
See Caution and Disclaimer on other side.

Typical Firing Profile for 5571



5571 1004-A

*None of the six substances referred to in the RoHS Directive (2002/95/EC) are used in the formulation of this product.

CAUTION: Proper industrial safety precautions should be exercised in using these products. Use with adequate ventilation. Avoid prolonged contact with skin or inhalation of any vapours emitted during use or heating of these compositions. The use of safety eye goggles, gloves or hand protection creams is recommended. Wash hands or skin thoroughly with soap and water after using these products. Do not eat or smoke in areas where these materials are used. Refer to appropriate MSDS sheet.

DISCLAIMER: The product information and recommendations contained herein are based on data obtained by tests we believe to be accurate, but the accuracy and completeness thereof is not guaranteed. No warranty is expressed or implied regarding the accuracy of these data, the results obtained from the use hereof, or that any such use will not infringe any patent. ElectroScience assumes no liability for any injury, loss, or damage, direct or consequential, arising out of its use by others. This information is furnished upon the condition that the person receiving it shall make his own tests to determine the suitability thereof for his particular use, before using it. User assumes all risk and liability whatsoever in connection with his intended use. ElectroScience's only obligation shall be to replace such quantity of the product proved defective.