



# Electro-Science Laboratories, Inc.

416 East Church Road • King of Prussia, PA 19406-2625, U.S.A  
610-272-8000 • Fax: 610-272-6759 • www.ElectroScience.com • Sales@ElectroScience.com

## CERMET PLATINUM GOLD CONDUCTOR

## 5800-B

ESL 5800-B is a general purpose platinum gold paste exhibiting good solderability and adhesion to alumina as well as excellent solder leach resistance. ESL 5800-B is used where severe environmental and bonding requirements must be met. It retains solder-to-lead-wire bond strength during long storage at elevated temperatures. Additionally, ESL 5800-B has been successfully used as a resistor termination and as an electrode for thick film capacitors.

### PASTE DATA

<b>RHEOLOGY:</b>	Thixotropic, screen printable paste
<b>VISCOSITY:</b> (Brookfield RVT, ABZ Spindle, 10 rpm, 25.5°C±0.5°C)	300±25 Pa·s
<b>BONDING MECHANISM:</b>	Mixed
<b>SHELF LIFE:</b> (25°C)	6 months

### PROCESSING

<b>SCREEN MESH/EMULSION:</b>	325/25 µm
<b>LEVELING TIME:</b> (25°C)	5-10 minutes
<b>DRYING TIME AT 125°C:</b>	10-15 minutes
<b>FIRING RANGE:</b>	850°C-980°C
<b>OPTIMUM:</b>	930°C
<b>TIME AT PEAK:</b>	10-12 minutes
<b>RATE OF ASCENT/DESCENT:</b>	60°C-100°C/minute
<b>SUBSTRATE OF CALIBRATION:</b>	96% alumina
<b>THINNER:</b>	ESL 401

5800-B 9710-C

#### ESL Affiliates

Japan: ESL-Nippon Company, Ltd. • Sukegawa Bldg. • 6<sup>th</sup> floor • 3-4 Yanagibashi 1-chome • Taito-ku • Tokyo 111, Japan • Tel: (011-81)-3-3864-8521 • Fax: (011-81)-3-3864-9270  
NipponSales@ESLNippon.com

China: Shanghai Agmet Electro-Science Laboratory Ltd. • Second Floor Bldg. 12A1 • #223 North Fe Te Road • Waigaoqiao Free Trade Zone • Shanghai, China  
Tel: (011-86)-21-5866-0497 • Fax: (011-86)-21-5866-0497 • ShanghaiSales@ShanghaiESL.com

Europe: Agmet, Ltd. • 8 Commercial Road • Reading, Berkshire, England RG2 0QZ • Tel: (011-44)-118-987-3139 • Fax: (011-44)-118-986-7331 • Sales@ESLEurope.co.uk

See Caution and Disclaimer on other side.

## TYPICAL PROPERTIES

<b>FIRED THICKNESS:</b>	10-18 $\mu\text{m}$
<b>APPROXIMATE COVERAGE:</b>	50-60 $\text{cm}^2/\text{gram}$
<b>RESISTIVITY:</b>	60-100 $\text{m}\Omega/\text{square}$
<b>PRINTING RESOLUTION:</b> (line/space)	250 $\mu\text{m}$ x 250 $\mu\text{m}$
<b>SOLDER WETTABILITY:</b> (RMA flux, 5 sec., dip, 62 Sn/36 Pb/2 Ag, 220°C $\pm$ 5°C)	Excellent
<b>SOLDER LEACH:</b> (No of 10 sec. dip to double resistance of 0.25 mm wide x 100 mm long conductor 63 Sn/37 Pb, 250°C $\pm$ 5°C)	12-14 dips
<b>ADHESION:</b> (90° pull, 2.0 x 2.0 mm pads, 63 Sn/37 Pb)	
<b>Initial pull strength:</b>	$\geq 50$ N
<b>Aged 48 hours at 150°C:</b>	$\geq 25$ N

5800-B 9710-C

---

**CAUTION:** Proper industrial safety precautions should be exercised in using these products. Use with adequate ventilation. Avoid prolonged contact with skin or inhalation of any vapors emitted during use or heating of these compositions. The use of safety eye goggles, gloves or hand protection creams is recommended. Wash hands or skin thoroughly with soap and water after using these products. Do not eat or smoke in areas where these materials are used. Refer to appropriate MSDS sheet.

**DISCLAIMER:** The product information and recommendations contained herein are based on data obtained by tests we believe to be accurate, but the accuracy and completeness thereof is not guaranteed. No warranty is expressed or implied regarding the accuracy of these data, the results obtained from the use hereof, or that any such use will not infringe any patent. Electro-Science assumes no liability for any injury, loss, or damage, direct or consequential arising out of its use by others. This information is furnished upon the condition that the person receiving it shall make their own tests to determine the suitability thereof for their particular use, before using it. User assumes all risk and liability whatsoever in connection with their intended use. Electro-Science's only obligation shall be to replace such quantity of the product proved defective.

---