



Electro-Science Laboratories, Inc.

416 East Church Road • King of Prussia, PA 19406-2625, U.S.A
610-272-8000 • Fax: 610-272-6759 • www.ElectroScience.com • Sales@ElectroScience.com

CONDUCTIVE ELECTRODE MATERIAL

9516

PLATINUM SILVER BASED CONDUCTOR DESIGNED FOR USE WITH THE 4150 SERIES AND 4200-C SERIES OF DIELECTRICS

ESL 9516 is a platinum silver based conductor specially developed for use as an electrode with 4150 Series and 4200-C Series of dielectrics. ESL 9516 may also be used with the 4100 Series of dielectrics. When used with ESL 4150 Series and 4200-C Series dielectrics, this conductor provides the optimum performance of the systems. The typical properties of these conductors were derived from printing and firing directly on alumina.

PASTE DATA

RHEOLOGY:	Thixotropic, screen printable paste
VISCOSITY: (Brookfield RVT, ABZ Spindle, 10 rpm, 25.5°C±0.5°C)	200±25 Pa·s
SHELF LIFE: (25°C)	6 months

PROCESSING

SCREEN MESH/EMULSION:	325/25 µm
LEVELING TIME: (25°C)	5-10 minutes
DRYING AT 125°C:	10-15 minutes
FIRING TEMPERATURE RANGE:	850°C-900°C
OPTIMUM:	900°C
TIME AT PEAK:	10 minutes
RATE OF ASCENT/DESCENT:	60°C-100°C/minute
SUBSTRATE OF CALIBRATION:	96% alumina
THINNER:	ESL 401 or 413

9516 9911-A

ESL Affiliates

Japan: ESL-Nippon Company, Ltd. • Sukegawa Bldg. • 6th floor • 3-4 Yanagibashi 1-chome • Taito-ku • Tokyo 111, Japan • Tel: (011-81)-3-3864-8521 • Fax: (011-81)-3-3864-9270
NipponSales@ESLNippon.com

China: Shanghai Agmet Electro-Science Laboratory Ltd. • Second Floor Bldg. 12A1 • #223 North Fe Te Road • Waigaoqiao Free Trade Zone • Shanghai, China
Tel: (011-86)-21-5866-0497 • Fax: (011-86)-21-5866-0497 • ShanghaiSales@ShanghaiESL.com

Europe: Agmet, Ltd. • 8 Commercial Road • Reading, Berkshire, England RG2 0QZ • Tel: (011-44)-118-987-3139 • Fax: (011-44)-118-986-7331 • Sales@ESLEurope.co.uk

See Caution and Disclaimer on other side.

TYPICAL PROPERTIES

FIRED THICKNESS:	12.5±2.5 µm
PRINTING RESOLUTION: (Line/Space)	125 µm/125 µm
RESISTIVITY:	≤ 3.2 mΩ/sq.
SOLDER LEACH: (No. of 10 sec. dips to double resistance of 0.25 mm wide x 100 mm long conductor, 62 Sn/36 Pb/2 Ag, 220°C±5°C)	≥ 10
ADHESION: (90° pull, 2.0 mm x 2.0 mm pads, 62 Sn/36 Pb/2 Ag, 220°C±5°C)	
Initial pull strength:	≥ 75 N
Aged 48 hours at 150°C:	≥ 50 N

9516 9911-A

CAUTION: Proper industrial safety precautions should be exercised in using these products. Use with adequate ventilation. Avoid prolonged contact with skin or inhalation of any vapors emitted during use or heating of these compositions. The use of safety eye goggles, gloves or hand protection creams is recommended. Wash hands or skin thoroughly with soap and water after using these products. Do not eat or smoke in areas where these materials are used. Refer to appropriate MSDS sheet.

DISCLAIMER: The product information and recommendations contained herein are based on data obtained by tests we believe to be accurate, but the accuracy and completeness thereof is not guaranteed. No warranty is expressed or implied regarding the accuracy of these data, the results obtained from the use hereof, or that any such use will not infringe any patent. Electro-Science assumes no liability for any injury, loss, or damage, direct or consequential arising out of its use by others. This information is furnished upon the condition that the person receiving it shall make their own tests to determine the suitability thereof for their particular use, before using it. User assumes all risk and liability whatsoever in connection with their intended use. Electro-Science's only obligation shall be to replace such quantity of the product proved defective.
