



ESL ELECTROSCIENCE

CERAMIC TAPES &
THICK-FILM MATERIALS

416 EAST CHURCH ROAD
KING OF PRUSSIA, PA 19406-2625, U.S.A

T: 610-272-8000
F: 610-272-6759

www.electroscience.com

CERMET SILVER CONDUCTOR

9912-K

Lead, Cadmium and Nickel-Free*

ESL 9912-K is a silver conductor having a wide range of applications, for example chip resistors, consumer hybrids, potentiometers and heaters. Due to the wide firing temperature range, this conductor may be processed onto a variety of substrates including glass, Porcelain Enamelled Steel (PES), alumina and special ceramics. Additionally, 9912-K also exhibits excellent gold wire bondability.

PASTE DATA

| | |
|---|-------------------------------------|
| Rheology: | Thixotropic, screen-printable paste |
| Viscosity: (Brookfield RVT, 10rpm, ABZ Spindle, 25.5 ± 0.5 °C) | 200 ± 25 Pa.s |
| Bonding Mechanism: | Mixed-bonded |
| Shelf Life (20 - 25 °C): | 6 months |

PROCESSING

| | |
|-----------------------------------|---|
| Screen Mesh, Emulsion: | 325 S/S, 25 µm |
| Levelling Time (at 20°C): | 5 - 10 min |
| Drying Time (at 125°C): | 10 - 15 min |
| Firing Temperature Range: | On alumina/beryllia/ceramics: 850 - 930°C in air On Porcelain Enamelled Steel (PES): 625°C in air Optimum (alumina): 850°C in air Optimum (beryllia): 930°C in air Time at peak: 10 min |
| Total Firing Cycle: | 1 hour |
| Substrate for Calibration: | 96% alumina |
| Thinner: | ESL 401 |

(Note: furnace air must be clean, dry and oil-free)

ESL Europe 9912-K 0601-E

ESL Affiliates

ESL Europe (Agmet Ltd) • 8 Commercial Road, Reading, Berkshire, RG2 0QZ, England • Tel: +44 (0) 118 918 2400 • Fax: +44 (0) 118 986 7331 • Sales@ESLEurope.co.uk

ESL Nippon • Sukegawa Bldg. 6th floor, 3-4 Yanagibashi 1-chome, Taito-ku, Tokyo 111, Japan • Tel: +81-3-3864-8521 • Fax: +81-3-3864-9270 • Sales@ESL-Nippon.co.jp

ESL China • Room #2712, Far East International Plaza, No.317 Xianxia Road, Changning District, Shanghai, China 200051 • Tel: +86-21-6237-0336 • Fax: +86-21-6237-0338 • ESLChina@eslshanghai.net

ESL Taiwan • 14F, No. 168, Tun Hwa N. Road, Sungsan District, Taipei, Taiwan • Tel: +886-975-553-612 • dshih@esl-taipei.com

ESL in Korea • AMT, #109-405, 85(4/2), Bakdal 2-Dong, Manan-Ku, Anyang-Si, KyunggiDo, South Korea • Tel: +82-31-466-0651 • Fax: +82-31-466-0658 • yumikim@esl-amt.co.kr

See Caution and Disclaimer on next page.

TYPICAL PROPERTIES

(measurement on alumina after firing at 850°C)

Fired Thickness: 11.5 ± 2.5 µm
(measured on a 2 mm x 2 mm pad on 96% alumina)

Approximate Coverage: 100 - 125 cm²/g

Resistivity: < 2.5 mΩ/□
(measured on a 100 mm x 0.25 mm conductor track at 12.5 µm fired thickness)

Printing Resolution: 0.200 mm / 0.200 mm
(line/space)

Adhesion:
(90° pull, 2 mm x 2 mm pads, 62Sn/36Pb/2Ag)

Initial pull strength: > 7.0 kg
(on most ceramic substrates)
Aged 48 hours at 150°C: > 4.5 kg

Thermosonic Au Wire Bond: > 8 g
(25 µm wire; bond length 1 mm;
100% wire breaks; on alumina; 850°C firing)

Aged Au Wire Bond: > 7 g
(24 hours at 200°C)

ESL Europe 9912-K 0601-E

*None of the six substances referred to in the RoHS Directive (2002/95/EC) are used in the formulation of this product.

CAUTION: Proper industrial safety precautions should be exercised in using these products. Use with adequate ventilation. Avoid prolonged contact with skin or inhalation of any vapours emitted during use or heating of these compositions. The use of safety eye goggles, gloves or hand protection creams is recommended. Wash hands or skin thoroughly with soap and water after using these products. Do not eat or smoke in areas where these materials are used. Refer to appropriate MSDS sheet.

DISCLAIMER: The product information and recommendations contained herein are based on data obtained by tests we believe to be accurate, but the accuracy and completeness thereof is not guaranteed. No warranty is expressed or implied regarding the accuracy of these data, the results obtained from the use hereof, or that any such use will not infringe any patent. ElectroScience assumes no liability for any injury, loss, or damage, direct or consequential, arising out of its use by others. This information is furnished upon the condition that the person receiving it shall make his own tests to determine the suitability thereof for his particular use, before using it. User assumes all risk and liability whatsoever in connection with his intended use. ElectroScience's only obligation shall be to replace such quantity of the product proved defective.
